







Typical Precast Finishes with GlassOx™

			
10x40	20x40	40x70	70x100
Coarse	Medium Coarse	Medium	Fine ("Acid Etch")

***NOTICE:** Results may vary based on curing, cement content, aggregate, blast equipment settings, and technique. Always conduct a test blast to ensure desired, consistent results.

GlassOx™ is a clean, carefully graded abrasive media suitable for ordinary or colored cements. You get clean, consistent finishes with no streaking or discoloring embedments, rogue peaks, or valleys. GlassOx™ is the safe alternative to sand and slags if you're looking to comply with OSHA regulations on beryllium or crystalline silica.

Recommendations

- Excellent for dry or wet blasting applications.
- 90 PSI at the nozzle
- 18 to 36 inches stand-off